

BASIC GUNNING MATERIAL

BRAND	MgO% (min)	Cr ₂ O ₃ % (Min)	SiO ₂ %	Setting	Grading (mm)	Sintering Temp °C	Application Temp °C	PLC @ 1550°C / 2hrs (Max)	Remarks
OR-GUN82	82	-	8	CHEMICAL	0-3	-	1750	-2	Gunning Material For EAF
OR-GUN84	84	-	6.5	CHEMICAL	0-3	-	1750	-2	Superior to Above
OR-SUPER ARC GUN	90	-	4	CHEMICAL /CERAMIC	0-4	-	1850	-1.5	Superior Gunning material to BOF / EAF
OR-TUNDISH COAT	80	-	7	-	0-2	-	1750	-	Tundish Spray- mix for wear lining
OR-TUNDISH SPRAY MIX	65	-	24	-	0-0.5	800	1600	-2.5	Wall & bottom of Tundish, spraying for worn out lining
OR-HOT PATCH	87 (% on loss free Basis)	-	6.5	CHEMICAL /CERAMIC	0-2 & 0-4	-	1750	-	for LD & Ladle EAF & EOI patching in Hot Condition
OR-EBT FILL	85	-	6.5	-	0-5	-	-	-	For use in low capacity and high capacity EBTS mass for smooth opening.
OR-EBT FILL SPL	90	-	5	-	0-5	-	-	-	-

WE CAN TAILOR MAKE GRADING & COMPOSITION AS PER THE CUSTOMERS REQUEST