


# SLIDE GATE REFRACTORIES & INSULATION CASTABLES



BRAND	AL <sub>2</sub> O <sub>3</sub> % ( Min )	Grading mm	Sintering Temp °C	Type of Setting	Remarks
OL LAYMORE- 70K	69	0-0.5	1200	CERAMIC	For fixing ladle nozzle with well block
OL LAYMORE 90K	88	0-0.5	1200	CHEMICAL /CERAMIC	for joining plate to nozzle
OR LAYCAST- 95H	93	0-4	1400	HYDRAULIC	for fixing well block to ladle